


Technical Data Sheet

eurocrete TC

High-Performance Polyurethane Cement Sealer
(Formerly TF)

Eurocrete TC is a high-performance, pigmented polyurethane cement sealer, applied at a thickness of 6–12 mils per coat. It provides exceptional durability and versatility, serving as a topcoat sealer for Eurocrete heavy, medium, and light-duty polyurethane cement systems, including those with fully broadcast aggregate overlays.



Classic Red



Grey



Chemical Resistant

Resistant to fats, oils, blood, sugar, and acids.



Slip Resistant

Positive texture to minimize slip hazards in wet environments.



Physical Resistance

Resistant to wheeled traffic, impacts, and abrasive use.



Easily Cleaned

Cleaning can be done with any method and any materials.

Physical Data

Tensile Strength:	ASTM C 307	2200 psi
Flexural Strength:	ASTM C 580	4500 psi
Coefficient of Thermal Expansion:	ASTM D 2047	1.1 x 10 ⁻⁵ in/in/°F
Abrasion Resistance:	ASTM D 4060 CS 17 Wheel, 1000 cycles	0.08g loss
Adhesion	ASTM D 4541	4.5 MPa (substrate failure)
Softening Point:		126°C / 260°F

Cure Schedule

Time to light traffic:	12 - 18 hr
Time to light wheels:	18 - 24 hr
Time to normal traffic:	24 hr

Times listed are for 20°C ambient temperature and 10 mil build.

Applications

eurocrete TC is the most suitable alternative to conventional epoxy thin mil floor systems due to its resistance to thermal shock, cleanliness and resistance to physical wear.

Installation

Refer to Installation Guide.

Physical & Chemical Resistance

eurocrete TC does not support microbial growth, and has physical properties which are approximately the same as the concrete substrate. It will tolerate a wide range of organic and inorganic acids, alkalis, and salts. It has a high bond strength that can withstand hot water cleaning.

Cleaning & Maintenance

Cleaning is straightforward and can be done with any method and any materials. Regular cleaning is recommended in order to maintain a slip resistant, enhanced appearance and to reduce any tendency to retain dirt. Normal cleaning agents in combination with hot water is acceptable.

Health & Safety

See SDS sheets.

Appearance

eurocrete TC is a squeegee and back roller applied coating.

This system produces a smooth yet anti-slip surface with a matte finish.

Durability

eurocrete TC has excellent chemical resistance, and its surface profile ensures slip resistance, even in wet process areas. It is impervious to light impact, abrasion, and a wide range of chemicals.

Substrates

The success of our flooring system is dependent upon the proper preparation of the concrete substrate. Diamond grinding is the preferred method since it abrades the substrate to remove any latent materials that could impede adhesion while maintaining a consistent abrasion pattern on the substrate,.

Thickness

It is generally applied between 8 - 12 mil thick.

eurocrete is a division of Bedford Industries Ltd.
PO Box 573 Fort Langley, BC V1M 2R9
Tel: 604-513-5855
Chemtrec 24 hour hotline: 1-800-424-9300
Sales@eurocrete.com
www.eurocrete.com